



**PRODUCTS**

Division of Sierra Corporation  
ISO 9001:2008 Certified

# TK-HYDROMAX 2001 DAMPPOOF COATING

Meets Federal EPA's VOC Requirements

## Technical Data

### 1. PRODUCT NAME

TK-HydroMax 2001 Dampproof Coating

### 2. MANUFACTURER

TK PRODUCTS  
DIVISION OF SIERRA CORPORATION  
11400 West 47th Street  
Minnetonka, MN 55343  
952-938-7223  
952-938-8084 (FAX)  
E-mail: tkproduct@aol.com  
Website: <http://www.tkproduct.com>

### 3. PRODUCT DESCRIPTION

TK-HydroMax 2001 Dampproof Coating is a plastic solution formulation intended to damp proof poured concrete, CMU and precast foundation walls for below grade applications. It may be used for residential and commercial foundations. It prevents the penetration of water and other chemicals. TK-HydroMax 2001 Dampproof Coating is intended to be applied to the exterior of the wall, but because it is a neutral pearl gray color, it may also be applied to the interior wall as a decorative and moisture/vapor retarding coating.

### 4. TECHNICAL DATA

TK-HydroMax 2001 Dampproof Coating is a single component liquid applied foundation coating that is non-breathable and non-elastomeric.

#### Composition and Materials:

*Hydrocarbon Resin / Polystyrene in aromatic hydrocarbon blend solvent.*

Solids Content:	46 - 47%
Color:	Pearl Gray
Flash Point:	Flammable, less than 100°F
Drying Time:	
Tack Free:	1 hour (recoat 2-4 hrs)
Full Cure:	4-8 hours

### Applicable Standards

TK-HydroMax 2001 Dampproof Coating meets or exceeds the following standards:

- ASTM E96-92 Permeability
- ASTM D 412-92 Tensile Strength and Elongation
- ASTM D 3359-93 Adhesion
- ASTM D 579-81 Long Term Moisture Penetration
- ASTM D570-81 Water Absorption
- ASTM D4541-93 Bond Strength
- ASTM D522-88 Flexibility
- VOC Content: Less than 600 grams per liter.
- A.I.M. Category: Waterproofing Sealer and Treatment - maximum VOC 600g/l.
- A.I.M. Definition: A coating formulated and recommended for application to a porous substrate for the primary purpose of preventing the penetration of water.
- USDA authorization for use in meat, poultry and food processing plants.

### 5. APPLICATION PROCEDURES AND INSTRUCTIONS

#### Preparation:

Material is ready for use and requires no mixing unless signs of separation are observed. It is unlawful to further reduce with non-exempt solvents.

A clean, dry, surface is required. New concrete should be allowed to cure until the surface appears dry. Surface should be frost free. Concrete block laid and walls poured late in the year should be allowed to gain sufficient strength for good adhesion. Existing concrete surfaces must be thoroughly cleaned prior to application. All previous coatings must be removed.

All masonry block and poured concrete voids, form tie holes, cracks, honeycombed areas should be filled and footings cleaned. Mortar smears, dirt and form release agents that will affect adhesion should be removed. TK-HydroMax 2001 Dampproof Coating should be applied directly to the clean dry concrete surface.

### Application:

A typical sprayer is a Graco 733/833 45:1 airless with a 0.037 tip. Brush and/or roller will also work.

### Coverage:

Coverage rate is inversely affected by the texture and porosity of the substrate. One coat is sufficient at 45-63 sq. ft. per gallon (25-36 wet mils = 10-13 dry mils). Typical applications for tight block walls are 45-50 sq. ft. per gallon. Typical applications for poured walls is 63 sq. ft. per gallon. Any area that is thin can be recoated.

The wall can be back filled once the film is cured. No protection board is required, if carefully backfilled with granular material with no large and/or frozen chunks that will puncture the coating.

### Limitations:

TK-HydroMax 2001 Dampproof Coating can be applied at 0° F to 100° F.

### Cleanup of Equipment:

Use TK-00 Solvent. For sprayer, pump the solvent through the spray equipment to remove residue of materials which can clog the hose and wand assembly.

### Precautions:

TK-HydroMax 2001 Dampproof Coating contains flammable solvents. Keep away from heat and flame. Prevent build-up of vapors. Use only with adequate ventilation. Do not breathe vapor or spray mist. If you experience eye watering, headaches or dizziness or if air monitoring demonstrates vapor/mist levels are above applicable limits, increase fresh air or wear an appropriate, properly fitted respirator (NIOSH/MSHA approved) during and after application. Close container after each use. Avoid contact with eyes, skin, and clothing. Wash after handling. KEEP OUT OF REACH OF CHILDREN. Do not allow vapors to penetrate into foodstuffs.

TK-HYDROMAX 2001  
Dampproof Coating

TK  
3  
PRODUCTS



TK  
3  
PRODUCTS

TK-HYDROMAX 2001  
Dampproof Coating

TK-HydroMax 2001 Dampproof Coating in its cured state is not toxic.

**First Aid:**

If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical assistance immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention immediately; for skin, wash thoroughly with soap and water. If swallowed, do not induce vomiting. Call physician immediately.

**In Case of Fire:**

Use foam, CO2, dry chemical. Do not use water spray. Generic Name: Petroleum Distillates.

**Spills or Leaks:**

Contain spilled material and remove with inert absorbent. Dispose of contaminated absorbent, container and unused content in accordance with local, state and federal regulations.

**6. AVAILABILITY**

TK-HydroMax 2001 Dampproof Coating is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in: 55-gallon drums and 5-gallon pails.

**Maintenance**

Minimal maintenance is required. If weathering occurs to the exposed area, TK-HydroMax 2001 Dampproof Coating can be reapplied to the affected area.

**7. CONDITIONS OF SALE/ LIMITED WARRANTY**

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. **SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.**

**8. TECHNICAL SERVICES**

The TK office offers assistance with specifications, performance test data and field services.

**9. FILING SYSTEMS**

Information Handling Services  
PO Box 1213  
Englewood, CO 80150  
Information Marketing Services  
13271 Northend  
Oak Park, MI 48237

**TK DISCLAIMER:**

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.

**FOR INDUSTRIAL USE ONLY**

12/09

Applicable Standards	TK-HydroMax 2001 Performance
ASTM E96-92 - Permeability	0.8 perms (grains/hr. ft <sup>2</sup> in Hg)
ASTM D 412-92 - Tensile Strength and Elongation	881 PSI, 2%
ASTM D 3359-93 - Adhesion	5A - No peeling or removal
ASTM D 579-81 - Long Term Moisture	4.22 WT%
ASTM D570-81 - Water Absorption	0.38 WT%
ASTM D4541-93 - Bond Strength	340 PSI
ASTM D522-88 - Flexibility	