

PRODUCT DESCRIPTION

TK-TRI-SHEEN PIGMENTED STAIN 5272 is a low viscosity, semi-opaque, acrylic emulsion designed for cementitious and wood surfaces. Its acrylic resins and unique formulation create a uniformly colored finish that lasts. Available in standard and custom color options.

Features:

- Provides color uniformity and long-lasting color retention.
- Breathable film allows trapped moisture to pass through successfully without loosening or peeling the coating.
- Odor free and VOC compliant, making it ideal for both interior or exterior applications.
- Acts as a protective shield against substrate damage due to abrasion, weathering and surface degradation.

USES:

Suitable for interior or exterior use on bush-hammered concrete, precast panels, concrete form liners, stucco, brick, block, stone, wood, or any properly prepared above-grade vertical surface. Ideal for creating color uniformity on multi-color applications, or for interior use on vertical applications where solvent-based systems cannot be used.

APPLICATION PROCEDURES

PREPARATION:

Suggested methods of surface preparation are power washing using a minimum of 3000 psi or greater, or by sandblasting, sanding or wire brushing. Any foreign matter including waxes, mildew and previous loose coatings must be removed before applying. TK-TRI-SHEEN PIGMENTED STAIN 5272 should only be applied to dry, sound and frost-free surfaces. Any repairs such as filling of bug holes and cracks or cleaning/removal of mortar should be complete prior to application.

A test area of 150 square feet should be applied to the prepared surface to check for surface qualification, adhesion and color approval before proceeding with full application.

MIXING:

TK-TRI-SHEEN PIGMENTED STAIN 5272 should be stirred for 5-10 minutes using a low-speed agitation mixer. When multiple containers are to be used, blend together (or "box") as necessary to ensure uniform color throughout the job.

APPLICATION:

TK-TRI-SHEEN PIGMENTED STAIN 5272 should be applied as a stain, rather than as a heavy paint-like coating. Apply with brush, roller or sprayer. If an airless sprayer is to be used, it should have a tip size of .015" - .018" with a 40°- 60° fan. If rolling, use care not to load an excessive amount of material on the surface as it should result in a thin, even coat. The final appearance of the product should be that of a uniformly colored surface without streaks or thin spots.

TECHNICAL DATA

Composition and Materials:	A 100% acrylic resin suspended in an aqueous emulsion with inorganic oxide tinting pigments for long-term color stability.
Non-Volatile Content:	29.3%
Weight per Gallon:	10.51
Viscosity:	66-70
Initial Gloss:	4% @ 60° max.
Dry Film Thickness:	1.0-1.5 mils
Flash Point:	None
Reduction:	None, ready to use
Dry Time*	To 30-45 minutes
Touch:	2 hours
	Recoat: 24-48 hours
	Full Cure:
VOC Content:	< 100 g/l
A.I.M. Category:	Stains, Opaque Maximum VOC 350 g/l

*Cooler temperatures and higher humidity rates will extend dry times

TESTING DATA

ASTM G155 - Accelerated Weathering:	- No checking/blistering/chalking/color change after 2400 hours - 5A adhesion rating after 2400 hours
ASTM B117 - Resistance to Salt Spray	- No film defect after 500 hours of exposure
ASTM D2794 - Impact Resistance:	- No film chipping after 80 inch-pounds of direct impact
ASTM D522 Method B - Flexibility:	- No cracking/breaking/etc. after 1/8" diameter mandrel
ASTM D2486 - Scrub Resistance:	- No failure after 740 cycles
ASTM D3359 - Adhesion Testing:	- No peeling/removal, classification 5A (Method A X-Cut Tape Test) - No film loss, classification 5B (Method B Cross-Cut Tape Test)
Resistance to Wind Driven Rain - Rilem Tube Method #11.4:	- Zero water penetration after 4 hours of exposure
Chemical Resistance:	- No softening or color change (10% Sodium Hydroxide) - No softening or color change (10% Ammonium Hydroxide)

Generally, only one coat is required. However, due to various substrates and application procedures, multiple coats may be necessary.

New Concrete Surfaces - Concrete must be 28 days old (at minimum) and should have had adequate time to fully dry before applying this product. Consult TK Products for application recommendations where concrete surfaces are less than 28 days old. Repair any surface defects, and remove any laitance of efflorescence before applying. If a curing compound has been used, it must either be removed or have fully dissipated. The surface pH should be tested, and must be at 12 or below at the time of application.

CLEAN UP:

Clean tools and equipment immediately with warm soapy water.

COVERAGE:

Surface	Coverage
Bush hammered concrete, precast panels and other cementitious surfaces	250-350 sq.ft./gal
Wood	200 sq.ft./gal

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

LIMITATIONS:

- Avoid application in direct sunlight or during extremely hot or windy conditions.
- Ambient air and surface temperatures should be at least 40°F at the time of application and should not fall below 40°F during the curing process.
- It is recommended that the coating be allowed 24 hours of cure time before being exposed to rain as heavy rain or down bursts may cause wash off of the material if not fully cured.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-TRI-SHEEN PIGMENTED STAIN 5272 is available through TK Distributors. Contact TK Products for the nearest distributor.

Available in standard and custom color options. Please submit custom color standards for pricing.

Packaged in 55-gallon drums and 5-gallon pails.

FOR PROFESSIONAL USE ONLY

04/17 Last Rev. 06/16

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.



TK Products Construction Coatings

11400 West 47th Street Minnetonka, MN 55343
800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com